



**What is claimed is**

1. A perfluoroelastomer article coated with a durable film comprising a polysiloxane and a urethane oligomer.
- 5 2. A perfluoroelastomer article of claim 1 wherein said film is of a thickness between 0.1 and 10 microns
3. A perfluoroelastomer article of claim 2 wherein said film is of a thickness between 3 and 7 microns
4. A perfluoroelastomer article of claim 1 wherein said polysiloxane is
- 10 a mixture of polysiloxanes of formulas




- wherein n and m are such that said polysiloxanes each have a number
- 15 average molecular weight between 500 and 5000, as measured by size exclusion chromatography employing polystyrene calibration standards.
  5. A perfluoroelastomer article of claim 1 wherein said urethane oligomer is based on an isocyanate of the formula




- 20 6. A process for forming a durable polysiloxane urethane oligomer film on a perfluoroelastomer article, said process comprising:
  - A. coating a cured perfluoroelastomer article with a dispersion comprising i) a polysiloxane having pendant hydroxyl groups
  - 25 and ii) a blocked isocyanate to form a wet-coated perfluoroelastomer article;

- B. drying said wet-coated perfluoroelastomer article to form a dry-coated perfluoroelastomer article at a temperature below which said pendant hydroxyl groups react with said blocked isocyanate to form urethane oligomer; and
- 5 C. heating said dry-coated perfluoroelastomer article to a temperature and for a sufficient period of time where said pendant hydroxyl groups react with said blocked isocyanate to form urethane oligomer and a durable film comprising said polysiloxane and urethane oligomer on the surface of said
- 10 perfluoroelastomer article.
7. A process of claim 6 wherein said polysiloxane is a mixture of polysiloxanes of the formulas



- 15 wherein n and m are such that said polysiloxanes each have a number average molecular weight between 500 and 5000, as measured by size exclusion chromatography employing polystyrene calibration standards.
8. A process of claim 6 wherein said isocyanate is of formula



9. A process of claim 6 wherein said dispersion has a weight ratio of polysiloxane to isocyanate between 9 to 1 and 1 to 1.
10. A process of claim 6 wherein said drying of said wet-coated perfluoroelastomer article takes place in air at 20°C.

DW0076 USNA

11. A process of claim 6 wherein said heating of said dry-coated perfluoroelastomer article is at a temperature greater than 100°C for more than 5 minutes.
  12. A process of claim 11 wherein said heating of said dry-coated
- 5 perfluoroelastomer article is at a temperature of 200°C for 10 minutes.